

BATYLINE®

Sport M2


WEIGHT: 380 g/sqm

POROSITY: ± 38 %


LENGTHS*: ± 50 Im



TRAMPOLINE



GYM MATS




GUARANTEES AND LABELS



ADVANTAGES

- EXCELLENT WELDABILITY
- **MESH FOR GYM MATS:**
SUITABLE FOR SPIKED SHOES
- **HIGH LEVEL OF SHOCK RESISTANCE**
- **HIGH TENSILE AND TEAR STRENGTH**
- **RESISTANCE TO MICRO-ORGANISMS**
- **HIGH FLEXIBILITY**

COLOURS & REFERENCES (COLOURS ARE INDICATIVE)



Ref.7452-6266

Ref.7452-6103

Ref.7452-5200

TECHNICAL SPECIFICATIONS

	BATYLINE® SPORT M2	STANDARDS
CORE YARN	1100 dtex PES HT	TERSUISSE
WEIGHT	380 g/sqm	EN ISO 2286-2
WIDTH	220 cm	
TENSILE STRENGTH (WARP/WEFT)	200/170 daN/5 cm	EN ISO 1421
ELONGATION AT RUPTURE	≤ 25%	EN ISO 1421
FLEXIBILITY TEST	≥ 60 mm	NF EN 1735
POROSITY	± 38%	
RESISTANCE TO MICRO-ORGANISMS	DEGREE 0, EXCELLENT	EN ISO 846 METHOD A AND B
EFFICIENCY IN WIND	68 %	XPG 39-100-3 MEASUREMENTS CARRIED OUT AT THE CMEFE IN GENEVA, SAMPLE 25 X 35 CM.
LIGHT FASTNESS	UVA 340 ≥ 7	QUVTEST EN ISO 11507
FLAME RETARDANCY	M2/NFP 92-507	
HANDLING TEMPERATURE RANGE	-30°C/+70°C	
QUALITY MANAGEMENT SYSTEM		ISO 9001
ENVIRONMENT MANAGEMENT SYSTEM		ISO 14001

The technical characteristics shown are average values given as a guide and may be modified.
*Our packaging data are given for information only and may vary as a function of manufacturing conditions.