

PRECONTRAIT® 392 S

WEIGHT: 820 g/sqm

POROSITY: ± 27 %

LENGTHS*: ± 50 lm



VENTILATION PARTITION



WINDBREAK



PERMANENT THERMAL PROTECTION

GUARANTEES AND LABELS



ADVANTAGES


- ▶ FERRARI® PRÉCONTRAIT® TECHNOLOGY
 - EXTRA THICK COATING = EXTENDED LIFESPAN
 - EXCELLENT WELDABILITY
 - STRAIGHT THREAD CONSISTENCY

- ▶ **CONSIDERABLE MECHANICAL STRENGTH**

COLOURS & REFERENCES (COLOURS ARE INDICATIVE)



Ref. 392-100S



Ref. 392-1075

TECHNICAL SPECIFICATIONS

	PRÉCONTRAIT® 392 S	STANDARDS
YARN	1100 dtex PES HT	TERSUISSE
WEIGHT	820 g/sqm	EN ISO 2286-2
WIDTH	180 cm	
TENSILE STRENGTH (WARP/WEFT)	300/300 daN/5 cm	EN ISO 1421
TEAR STRENGTH (WARP/WEFT)	60/60 daN	DIN 53.363
ADHESION	8/8 daN/5 cm	EN ISO 2411
FINISH	FORMULA S / FLUORINATED VARNISH WELDABLE (ONLY ON WHITE 100S)	
POROSITY	± 27%	
EFFICIENCY IN WIND	81%	XPG 39-100-3 MEASUREMENTS CARRIED OUT AT THE CMEFE IN GENEVA, SAMPLE 25 X 35 CM.
FLAME RETARDANCY	M2/NFP 92-507 • TEST 2/NFPA 701 • CSFM T19 • B1/DIN 4102-1 B1/ONORM B 3800-1 • M2/UNE 23.727 • VKF 5.3/SN 198898	
HANDLING TEMPERATURE RANGE	-30°C/+70°C	
QUALITY MANAGEMENT SYSTEM		ISO 9001

The technical characteristics shown are average values given as a guide and may be modified.
*Our packaging data are given for information only and may vary as a function of manufacturing conditions.