

PRECONTRAIT®

402

TRANSLUCENT

WIDTH: **267 cm**

WEIGHT: **490 g/sqm**

JUMBO ROLLS*: **± 350 lm**

LENGTHS*: **± 60 lm**



STRUCTURES COMMERCIALES

G U A R A N T E E S A N D L A B E L S



Anti-capillarity treatment




ADVANTAGES

- FERRARI® PRÉCONTRAIT® TECHNOLOGY:
 - EXCEPTIONAL DIMENSIONAL STABILITY
 - HIGH DURABILITY
 - EXCELLENT WELDABILITY
- EXCEPTIONAL LUMINOSITY
- ANTI-CAPILLARY TREATMENT
- BRIGHT WHITE
- **LIGHTWEIGHT AND HIGH STRENGTH COMBINATION:**
TEAR STRENGTH OF 250/250 daN/5 cm
FOR A WEIGHT OF ONLY 490 g/sqm!
- FOR APPLICATIONS IN AREAS WITH HIGH SUNLIGHT : PLEASE CONSULT US

COLOURS & REFERENCES

(COLOURS ARE INDICATIVE)



Ref. 402-1399

TECHNICAL SPECIFICATIONS

	PRÉCONTRAIT® 402	STANDARDS TERSUISSE
YARN	1100 dtex PES HT	
WEIGHT	490 g/sqm	EN ISO 2286-2
WIDTH	267 cm	
TENSILE STRENGTH (WARP/WEFT)	250/250 daN/5 cm	EN ISO 1421
TEAR STRENGTH (WARP/WEFT)	20/20 daN	DIN 53.363
ADHESION	8/8 daN/5 cm	EN ISO 2411
FINISH	VARNISH BOTH SIDES	
LIGHT TRANSMISSION	48 %	NFP 38.511
U.V. TRANSMISSION	4 %	EN 410
FLAME RETARDANCY	M2/NFP 92-507 • CSFM T19 • VKF 5.3/SN 198898 B1/DIN 4102-1 • BS 7837 • B1/ONORM B3800-1 M2/UNE 23.727 • LP7 • ROCT 30444	
HANDLING TEMPERATURE RANGE	-30°C/+70°C	
QUALITY MANAGEMENT SYSTEM		ISO 9001

The technical characteristics shown are average values given as a guide and may be modified.
*Our packaging data are given for information only and may vary as a function of manufacturing conditions.