

# PRECONTRAIN<sup>®</sup> 492 S

WEIGHT: 1000 g/sqm

POROSITY: ± 27 %

LENGTHS\*: ± 50 lm



VENTILATION PARTITION

TRAMPOLINES

SHADING

GUARANTEES AND LABELS



## ADVANTAGES

- FERRARI<sup>®</sup> PRÉCONTRAIN<sup>®</sup> TECHNOLOGY
  - EXTRA THICK COATING = EXTENDED LIFESPAN
  - EXCELLENT WELDABILITY
  - STRAIGHT THREAD CONSISTENCY

- **CONSIDERABLE MECHANICAL STRENGTH**

## COLOURS & REFERENCES

(COLOURS ARE INDICATIVE)



Ref. 492-100S

## TECHNICAL SPECIFICATIONS

	PRÉCONTRAIN <sup>®</sup> 492 S	STANDARDS
YARN	1670 dtex PES HT	TERSUISSE
WEIGHT	1000 g/sqm	EN ISO 2286-2
WIDTH	180 cm	
TENSILE STRENGTH (WARP/WEFT)	400/250 daN/5 cm	EN ISO 1421
TEAR STRENGTH (WARP/WEFT)	100/55 daN	DIN 53.363
ADHESION	12/12 daN/5 cm	EN ISO 2411
FINISH	FORMULA S / FLUORINATED VARNISH WELDABLE	
POROSITY	± 27%	
EFFICIENCY IN WIND	84%	XPG 39-100-3 MEASUREMENTS CARRIED OUT AT THE CMEFE IN GENEVA, SAMPLE 25 X 35 CM.
FLAME RETARDANCY	M2/NFP 92-507 • TEST 2/NFPA 701 • CSFM T19	
HANDLING TEMPERATURE RANGE	-30°C/+70°C	
QUALITY MANAGEMENT SYSTEM		ISO 9001

The technical characteristics shown are average values given as a guide and may be modified.

\*Our packaging data are given for information only and may vary as a function of manufacturing conditions.