

757/957/1257

WIDTH: 260 cm	WEIGHT: 750/950/1250 g/sqm
JUMBO ROLLS* ± 300 lm	ROLLS* ± 30 lm



POOL COVER



FLEXIBLE TANKS



GEOMEMBRANE

GUARANTEES AND LABELS



Stamfood® 757
(On request)




Stamfood® 957/1257
(On request)



ADVANTAGES

- **BOTH SIDES OF THE MEMBRANE COMPLY WITH EUROPEAN DIRECTIVES 2002/72/CE - 97/48/CE - 85/572/CE** ON MATERIAL SUITABLE FOR CONTACT WITH FOOD STUFF FREE OF FATS. AUTHORIZED FOOD STUFF LIST ON REQUEST
- **DRINKING WATER SANITARY CERTIFICATE (ACS)** FOR BOTH SIDES IN THE CASE OF CONTACT WITH DRINKING WATER.
- **SUITABLE FOR THE STORAGE OF DEMINERALISED WATER**
- **HYDROPHOBIC COATING** FOR A LONGER LIFE SPAN
- **U.V. PROOF FORMULA**
- **WEIGHT/STRENGTH RATIO**
- **2 COLOUR REVERSABLE MEMBRANE**

COLOURS & RÉFÉRENCES (COLOURS ARE INDICATIVE)



1 beige side and 1 white side

STAMFOOD® 757-20040
TYP I

STAMFOOD® 957-20040
TYP II

STAMFOOD® 1257-20040
TYP II

TECHNICAL SPECIFICATIONS

	STAMFOOD® 757	STAMFOOD® 957	STAMFOOD® 1257	STANDARDS
YARN	1100 dtex PES HT	2 x 1100 dtex PES HT	2 x 1100 dtex PES HT	TERSUISSE
WEIGHT	750 g/sqm	950 g/sqm	1250 g/sqm	EN ISO 2286-2
WIDTH	260 cm	260 cm	260 cm	
TENSILE STRENGTH (WARP/WEFT)	280/280 daN/5cm	400/400 daN/5cm	400/400 daN/5cm	EN ISO 1421
TEAR STRENGTH (WARP/WEFT)	25/25 daN	55/45 daN	55/45 daN	DIN 53.363
ADHESION	12/12 daN/5 cm	13/13 daN/5 cm	13/13 daN/5 cm	EN ISO 2411
HANDLING TEMPERATURE RANGE	-30°C/+70°C	-30°C/+70°C	-30°C/+70°C	
QUALITY MANAGEMENT SYSTEM				ISO 9001

The technical characteristics shown are average values given as a guide and may be modified.

*Our packaging data are given for information only and may vary as a function of manufacturing conditions.